

**Typical test results of Wire Rope Compound – HP Rodec 120**

Characteristics	Typical Test Results	Test Method
Appearance	Black	Visual
Flash Point, °C	>250	ASTM D 92
Drop Point, °C ,	84	ASTM D 127
Softening point, °C	65	ASTM D 127
Breaking Point, °C	-30	DIN 52012
Penetration (Needle), 1/10 mm @25 °C	20-25	ASTM D 1321
Content of water soluble corrosive acids	Free from water soluble corrosive acids	-
Processing temperature	110-130	-
Salt spray test, hrs. Pass	720 hrs.	ASTM B 117